

P.O.Mega Flex

Laminated Backlit


Digital Printing Materials By
PEOPLE
 OUTDOOR

Item	Unit	Value	Test Method
Base Fabric	Denier	500DX1000D	(High tenacity yarn) 100%PES
Construction	Weaving/inch	18x12	/
Weight of fabric	Gsm/m2	95±5	DIN53352 BS3424 Method5B
Weight of PVC	Gsm/m2	455±5	DIN53352 BS3424 Method5B
Total weight	Gsm/m2	550±10	DIN53352 BS3424 Method5A
Thickness	mm	0.46±0.02	DIN EN ISO 2286-3
Width	cm	Up to 500	/
Tensile Strength	N/5cm	Warp	1300
		Weft	1100
Tearing Strength	N	Warp	140
		Weft	110
Adhesion	N/5CM	60	DIN53357 BS3425 Method9B
Temperature Resistance	°C	-20~70	DIN53357 BS3425 Method10
Lacquering	If you need, we can lacquering with: 3555 (Acrylic), 3483 (Acrylic), 7584 (PVDF)		
Flammability	We can reach: B1, B2, NFPA701, DIN75200, etc.		
LOW CADMIUM & HEAVY METALS	We can reach: EN71-3		

Compatible With
 UV, Solvent, ECO Solvent, Latex
Printers



SignMAKER
 Solutions



Declaration by PEOPLE OUT DOOR: Please choose PEOPLE products suitably according to relative provisions or industrial standards. PEOPLE bears the responsibility for specified technical and performance data on this page only. PEOPLE is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable)