

P.O.Blockout 510g

Laminated Blockout

Digital Printing Materials By

PEOPLE
OUTDOOR

Item	Unit	Value	Test Method	
Base Fabric	Denier	300DX300D	(Domestic yarn) 100%PES	
Construction	Weaving/inch	18x18	/	
Weight of fabric	Gsm/m2	64±5	DIN53352 BS3424 Method5B	
Weight of PVC	Gsm/m2	446±5	DIN53352 BS3424 Method5B	
Total weight	Gsm/m2	510±10	DIN53352 BS3424 Method5A	
Thickness	mm	0.40±0.02	DIN EN ISO 2286-3	
Width	cm	102---320	/	
Tensile Strength	N/5cm	Warp	450	DIN53352 BS3424
		Weft	350	
Tearing Strength	N	Warp	55	DIN53356 BS3424
		Weft	50	
Adhesion	N/5CM	60	DIN53357 BS3425 Method9B	
Temperature Resistance	°C	-20~70	DIN53357 BS3425 Method10	
Lacquering	None			
Flammability	We can achieve: B1, B2, NFPA701, etc.			
LOW CADMIUM & HEAVYMETALS	We can be applied for : Cadmium free (EN7143) or Reach Compliance			

Compatible With

UV, Solvent, ECO Solvent, Latex

Printers



Digital Printing Materials By



Declaration by PEOPLE OUT DOOR: Please choose PEOPLE products suitably according to relative provisions or industrial standards. PEOPLE bears the responsibility for specified technical and performance data on this page only. PEOPLE is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable)